



ROCLAND

Roc Joint PU 920/925 Poliuretansko brtvilo

Opis proizvoda

Roc joint PU 920/925 poliuretansko brtvilo dolazi u tubama (ref 920) ili crijevima (ref 925) za ispunjavanje dilatacijskih fuga na betonskim podovima.

Roc joint PU 920/925 djeluje sa vlagom u zraku pri kojem se pretvara u fleksibilni spoj sa vrlo dobrim otporom na hydrocarbon i veliki dio kemijskih proizvoda.

Fizicka svojstva

Aspekt:	svijetlo siva pasta
Gustoća:	1.16 +/- 0,05
Vrijeme vezanja:	60 mn na 20 °C
Vrijeme sušenja:	3 mm/24 h na 20 °C
Temperatura nanošenja:	5 to 35 °C
Tvrdoća po Shoreu:	40 to 50
Temperaturna otpornost:	- 30 to + 60 °C
Izduženje pri pucanju:	> 300 %

Pakiranje i skladištenje

Roc joint PU 920 : 310 ml tube.

Roc joint PU 925 : 600 ml crijevo.

Skladištenje : 12 mjeseci u originalnom, hermetički zatvorenom pakiranju na temperaturi između 5 i 25°C.

Uputstva za upotrebu

Podloga mora biti čista, bez prašine, ulja, masti i bilo kakvih onečišćenja koje bi mogle naškoditi povezivanju.

Roc joint PU 920/925 može se nanjeti ručnim ili pneumatskim pištoljom. Nakon nanašanja, koristite kit nož za zaglađivanje spojeva.

Čišćenje: Alat bi se trebao čistiti acetonom

Potrošnja

Jedna tuba PU 920 (310 ml) za 4 mm široke, 7 mm duboke na 10 metara dužine.

20 crijeva PU 925 (600 ml) za 6 mm široke, 9 mm duboke na 100 metara dužine.

Zaštita na radu

Nije klasificirano kao opasno.

Pročitati sigurnosni materijal prije upotrebe.



Note :

Whilst all reasonable care is taken in compiling technical data on the company's products, all recommendations or suggestions regarding the use of such products are made without guarantee since the conditions of use are beyond the control of the company. It is the customer's responsibility to satisfy himself that each product is fit for the purpose for which he intends to use it and that the actual conditions of use are suitable.



Z.A. Les Monts du Matin
Rue des Lauriers
F-26730 La Baume d'Hostun
France
Office phone : + 33 4 75 48 37 50

www.roclang.eu
contact@roclang.eu